

AMENDMENTS TO THE CLAIMS:

The following listing of claims replaces all prior versions of the claims:

1. (Currently Amended) A fiber reinforced plastic pipe reduced in thickness and increased in diameter by pultrusion process, comprising
a fiber bundle ~~spun~~ which fibers are and aligned in a longitudinal direction, and
a single circumferential reinforced fiber sheet provided at least either on an outer surface layer or on an inner surface layer thereof.

2. (Currently Amended) A fiber reinforced plastic pipe reduced in thickness and increased in diameter by pultrusion process, comprising
a fiber bundle ~~spun~~ which fibers are and aligned in a longitudinal direction, and
a single circumferential reinforced fiber sheet provided at least either on an outer surface layer or on an inner surface layer thereof, wherein
the pipe has a slit, capable of being reduced in diameter along the circumference, provided in the longitudinal direction, such that said fiber reinforced plastic pipe can be inserted into a metal pipe.

3. (Previously Presented) The fiber reinforced plastic pipe according to claim 1 or 2, wherein
a tensile elasticity of fibers forming said fiber bundle is 196 GPa or more.

4. (Previously Presented) The fiber reinforced plastic pipe according to claim 1 or 2, wherein
a tensile elasticity of fibers forming said circumferential reinforced fiber sheet is 58.8 GPa or more.

5. (Previously Presented) The fiber reinforced plastic pipe according to claim 1 or 2, wherein

a basis weight (FAW) of said circumferential reinforced fiber sheet is in the range of 100 g/m² to 600 g/m².

6. (Previously Presented) The fiber reinforced plastic pipe according to claim 1 or 2, wherein

a thickness of said circumferential reinforced fiber sheet is in the range of 0.05 mm to 1.0 mm.

7. (Currently Amended) A power transmission shaft comprising a metal joint element and a metal pipe jointed to each other, wherein

the shaft further comprises a fiber reinforced plastic pipe inserted into said metal pipe, said fiber reinforced plastic pipe being reduced in thickness and increased in diameter by pultrusion process, comprising a fiber bundle ~~spun~~which fibers are and aligned in a longitudinal direction, and a single circumferential reinforced fiber sheet provided at least either on an outer surface layer or on an inner surface layer thereof.

8. (Currently Amended) A power transmission shaft comprising a metal joint element and a metal pipe jointed to each other, wherein

the shaft further comprises a fiber reinforced plastic pipe inserted into said metal pipe, said fiber reinforced plastic pipe being reduced in thickness and increased in diameter by pultrusion process, comprising a fiber bundle ~~spun~~which fibers are and aligned in a longitudinal direction, and a single circumferential reinforced fiber sheet provided at least either on an outer surface layer or on an inner surface layer, the pipe

having a slit, capable of being reduced in diameter along the circumference, provided in the longitudinal direction.

9. (Original) The power transmission shaft according to claim 8, wherein the slit has a width of 0.01% or more and 40% or less of the outer circumference thereof in a natural state.

10. (Original) The power transmission shaft according to claim 8 or 9, wherein said slit has a bias angle within ± 30 degrees with respect to an axial direction of said fiber reinforced plastic pipe.

11. (Original) The power transmission shaft according to claim 8, wherein a value of D_1/D_2 is greater than 1 and equal to 1.3 or less, where D_1 is an outer diameter of said fiber reinforced plastic pipe and D_2 is an inner diameter of said metal pipe.

12. (Previously Presented) The power transmission shaft according to claim 7 or 8, wherein

a tensile elasticity of fibers forming said fiber bundle is 196 GPa or more.

13. (Previously Presented) The power transmission shaft according to claim 7 or 8, wherein

a tensile elasticity of fibers forming said circumferential reinforced fiber sheet is 58.8 GPa or more.

14. (Previously Presented) The power transmission shaft according to claim 7 or 8, wherein

a basis weight (FAW) of said circumferential reinforced fiber sheet is in the range of 100 g/m^2 to 600 g/m^2 .

15. (Previously Presented) The power transmission shaft according to claim 7 or 8, wherein

a thickness of said circumferential reinforced fiber sheet is in the range of 0.05 mm to 1.0 mm.

16. (Original) The power transmission shaft according to claim 7 or 8, wherein said fiber reinforced plastic pipe has a layered structure of 20 layers or less.

17. (Original) The power transmission shaft according to claim 7 or 8, wherein a value of FL/PL is 0.1 or more and 1.0 or less, where PL is a length of said metal pipe and FL is a length of said fiber reinforced plastic pipe.

18. (Original) The power transmission shaft according to claim 7 or 8, wherein a value of t_2/t_1 is 0.01 or more and 10 or less, where t_1 is a thickness of said metal pipe and t_2 is a thickness of said fiber reinforced plastic pipe.

19. (Original) The power transmission shaft according to claim 7 or 8, wherein said fiber reinforced plastic pipe is fixed to said metal pipe by reducing said metal pipe in diameter along the outer circumference by plastic-working, with said fiber reinforced plastic pipe being inserted in said metal pipe.

20. (Original) The power transmission shaft according to claim 7 or 8, wherein said fiber reinforced plastic pipe is fixed to said metal pipe with an adhesive.

21. (Original) The power transmission shaft according to claim 20, wherein a recessed portion for accommodating adhesive is provided at least on any one of an outer circumference of said fiber reinforced plastic pipe or an inner circumference of said metal pipe.